



318 W. Washington Street  
Valders, WI 54245

Phone: 920-775-4151  
Fax: 920-775-4087

### Coefficient of Friction Test Data (CoF) - 4/09

Test Description	Sample	Finish	As Received	Cleaned	As Received	Cleaned	Average Result
			Dry	Dry	Wet	Wet	
ASTM C1028-07 Static Coefficient of Friction	Valders Dovewhite	Polished	0.75	0.84	0.52	0.50	<b>0.65</b>
		Honed	0.8	0.95	0.64	0.72	<b>0.78</b>
		Light Sandblast	1.07	1.11	0.79	0.86	<b>0.96</b>
ASTM C1028-07 Static Coefficient of Friction	Valders Gray	Polished	0.85	1.02	0.51	0.47	<b>0.71</b>
		Honed	0.76	1.02	0.72	0.69	<b>0.80</b>
		Light Sandblast	1.16	0.99	0.86	0.79	<b>0.95</b>
ASTM C1028-07 Static Coefficient of Friction	Valders Buff	Polished	0.91	0.91	0.56	0.50	<b>0.72</b>
		Honed	0.97	1.23	0.78	0.79	<b>0.94</b>
		Light Sandblast	1.05	1.2	0.86	0.94	<b>1.01</b>
ASTM C1028-07 Static Coefficient of Friction	Valders River Bluff	Polished	0.75	1.01	0.7	0.50	<b>0.74</b>
		Honed	0.85	1.08	0.65	0.60	<b>0.80</b>
		Light Sandblast	1.03	1.08	0.75	0.82	<b>0.92</b>

### Solar Reflectivity Index Test Data (SRI) - 4/09

Test Description	Valders Dovewhite Honed	Valders Gray Honed	Valders Buff Honed	Average Result
ASTM C1371-04a Thermal Emittance	0.89	0.89	0.90	<b>0.89</b>
ASTM C1549-04 Solar Reflectance	0.58	0.48	0.54	<b>0.53</b>

ASTM C1980-01 Solar Reflectance Index (SRI)	Valders Dovewhite Honed	Valders Gray Honed	Valders Buff Honed	Average Result
SRI: Low Wind	66	53	62	<b>60</b>
SRI: Medium Wind	68	55	64	<b>62</b>
SRI: High Wind	70	57	65	<b>64</b>
Individual Average	<b>68</b>	<b>55</b>	<b>64</b>	<b>62</b>