# Edon, STONE

# **EDEN OUTCROPPING FOR BENCHES**

## **PACKAGING**

Typically 3 to 4 pieces per pallet

### ASTM C97

Max. Water Absorption 0.20% Min. Density 170 pcf

### **ASTM C170**

Min. Compressive Strength 33,000 psi

### **GEOLOGY**

**Dolomitic Limestone** 

### ORIGIN

Eden, WI

### DESCRIPTION

Natural bedface top & bottom, Natural and irregular sides and ends

### COLOR

White to light gray and some buff, will buffen as it ages

### COVERAGE

Typically 6 to 8 sqft per ton (depending on installation)

### LENGTHS

Random 24 to 48 inches (610 to 1219 mm)

### **DEPTH**

Random 18 to 36 inches (457 to 914 mm)

### WEIGHT

Approximately 173 lbs per cubic foot

### **THICKNESS**

Random 16 to 24 inches (406 to 609 mm)

Eden-Valders Stone Company www.evstone.net

W4520 Lime Rd. Eden, WI 53019 (920) 477-2521 318 W Washington St. Valders, WI 54245 (920) 775-4151