



CHILTON LEDGESTONE (SPLITFACE)



PACKAGING

Full Veneer - 3000lbs or 4000lbs on wooden pallets with stretch wrap

Thin Veneer - Small boxes include 8 sqft per box for flats or 6 lnft per box for corners. Large crates include 120 sqft for flats or 70 lnft for corners.

ASTM C97

Water Absorption 0.11%

Density 173 pcf

ASTM C99

Modulus of Rupture 4,650 psi

ASTM C170

Compressive Strength 38,420 psi

GEOLOGY

Dolomitic Limestone

ORIGIN

Chilton, WI

DESCRIPTION

Machine splitface. Natural cleft top and bottom. Snapped ends.

COLOR

Grays, Slight Blue and Slight Lavender

COVERAGE

Full Veneer - Approximately 42 sqft per ton

LENGTHS

Random 8 to 36 inches (203 to 914 mm)

HEIGHTS

Full & Thin Veneer - 1 to 3 inches (25 to 76 mm)

WEIGHT

Approximately 173 lbs per cubic foot

THICKNESS

Full Veneer - 3-1/2 to 4-1/2 inches (89 to 114 mm) with some up to 5 inches (127 mm) maximum

Thin Veneer - 3/4 to 1-1/2 inches (19 mm to 38 mm)

Eden-Valders Stone
www.evstone.net

W4520 Lime Rd. Eden, WI 53019
(920) 477-2521

318 W Washington St. Valders, WI 54245
(920) 775-4151