



ASTM C97

Water Absorption 1.4%
Density 162 pcf

ASTM C99

Modulus of Rupture 1,855 psi

ASTM C170

Compressive Strength 29,400 psi

ASTM C880

Flexural Strength 1,560 psi

GEOLOGY

Dolomitic Limestone

ORIGIN

Valders, WI

DESCRIPTION

Sawn on all four sides

COLOR

Various Shades of Buff

WEIGHT

Approximately 162 lbs per cubic foot

THICKNESS

Cut per specification

TEXTURES

Honed, Polished, Sandblast, Flamed, Bushhammer

EDGE PREP

Cut per specification