



## VALDERS DOVEWHITE PANELS



### **ASTM C97**

Water Absorption 1.25%  
Density 165 pcf

### **ASTM C99**

Modulus of Rupture 2,420 psi

### **ASTM C170**

Compressive Strength 29,000 psi

### **ASTM C880**

Flexural Strength 1,800 psi

### **GEOLOGY**

Dolomitic Limestone

### **ORIGIN**

Valders, WI

### **DESCRIPTION**

Sawn on all four sides

### **COLOR**

Various Shades of Dovewhite

### **WEIGHT**

Approximately 165lbs per cubic foot

### **THICKNESS**

Cut per specification

### **TEXTURES**

Honed, Polished, Sandblast, Flamed, Bushhammer

### **EDGE PREP**

Cut per specification

Eden-Valders Stone  
[www.evstone.net](http://www.evstone.net)

W4520 Lime Rd. Eden, WI 53019  
(920) 477-2521

318 W Washington St. Valders, WI 54245  
(920) 775-4151