



ASTM C97

Water Absorption .4%
Density 172 pcf

ASTM C99

Modulus of Rupture 2,655 psi

ASTM C170

Compressive Strength 31,000 psi

ASTM C880

Flexural Strength 2,700 psi

GEOLOGY

Dolomitic Limestone

ORIGIN

Valders, WI

DESCRIPTION

Sawn on all four sides

COLOR

Various Shades of Gray

WEIGHT

Approximately 172 lbs per cubic foot

THICKNESS

Cut per specification

TEXTURES

Honed, Polished, Sandblast, Flamed, Bushhammer

EDGE PREP

Cut per specification